

PRODUCT INFORMATION

PLEXIGLAS® 7M

Product Profile:

PLEXIGLAS® 7M is based on polymethyl methacrylate (PMMA).

Besides showing the familiar properties of PLEXIGLAS® 7H molding compounds, such as

- excellent light transmission and brilliance
- excellent weatherability
- high mechanical strength, surface hardness and abrasion resistance.

PLEXIGLAS® 7M is special in that it

- better flowing behavior,
- AMECA listing.

Application:

PLEXIGLAS® 7M is particularly suitable for extruding profiles and panels for use in lighting engineering.

Examples:

lighting fixtures, displays and similar extruded items for technical purposes.

Processing:

PLEXIGLAS® 7M can be processed on extruders with 3-zone general purpose screws for thermoplastics.

Physical Form / Packaging:

PLEXIGLAS® molding compound is supplied as pellets of uniform size in two-ply, 25kg polyethylene bags; other packaging on request.

For more information:

For more information, e.g. Charts or lists of resistance are in the database CAMPUS® (<http://www.campusplastics.com>) free of charge.

Properties:

	Parameter	Unit	Standard	PLEXIGLAS® 7M
Mechanical Properties				
Tensile Modulus	1 mm/min	MPa	ISO 527	3200
Stress @ Break	5 mm/min	MPa	ISO 527	69
Strain @ Break	5 mm/min	%	ISO 527	4
Charpy Impact Strength	23°C	kJ/m²	ISO 179/1eU	20
Thermal Properties				
Vicat Softening Temperature	B / 50	°C	ISO 306	104
Glass Transition Temperature		°C	ISO 11357	108
Coeff. of Linear Therm. Expansion	0 - 50°C	E-5 /°K	ISO 11359	8
Flammability UL 94	1.5 mm	Class	IEC 60695-11-10	HB
Rheological Properties				
Melt Volume Rate, MVR	230°C / 3.8kg	cm³/10min	ISO 1133	2.9
Optical Properties				
Luminous transmittance	d=3 mm			
Luminous transmittance	D65	%	ISO 13468-2	92
Refractive Index	589nm/23°C		ISO 489	1.49
Other Properties				
Density		g/cm³	ISO 1183	1.19
Recommended Processing Conditions				
Predrying Temperature		°C		max. 94
Predrying Time in Desiccant-Type Drier		h		2 - 3
Melt Temperature		°C		220 - 260
Die Temperature (Extrusion)		°C		220 - 260

All listed technical data are typical values intended for your guidance. They are given without obligation and do not constitute a materials specification.

Certified to ISO 9001:2015, ISO 14001:2015 and IATF 16949:2016.

This information and all further technical advice is based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

Röhm is a worldwide manufacturer of PMMA products sold under the PLEXIGLAS® trademark on the European, Asian, African and Australian continents and under the ACRYLITE® trademark in the Americas.

® = registered trademark

PLEXIGLAS and PLEXIMID are registered trademarks of Röhm GmbH.

CAMPUS is a registered trademark of Chemie Wirtschaftsförderungs-GmbH, Frankfurt / M.

Röhm GmbH • Darmstadt • Germany
 plexiglas.polymers@roehm.com
 www.plexiglas-polymers.com
 www.roehm.com

Ref. No.: MC34-E A1142 Date: 2020-02-20