

PRODUCT INFORMATION

PLEXIGLAS® Heatresist FT15

Product Profile:

PLEXIGLAS® Heatresist FT15 is a special acrylic-based polymer.

With regard to its

- good weather resistance and
- high light transmission,

PLEXIGLAS® Heatresist FT15 shows comparable properties to those of PLEXIGLAS® standard molding compounds. In addition, PLEXIGLAS® Heatresist FT15 offers the special benefit of a

- high heat deflection temperature combined with good flow.

Application:

PLEXIGLAS® Heatresist FT15 is particularly suitable for injection moldings.

Examples:

luminaire covers, automotive lights and technical moldings exposed to high temperatures.

Processing:

PLEXIGLAS® Heatresist FT15 can be processed on injection-molding machines with for PMMA suitable 3-zone-screw. Good pre-desiccation must be pointed out.

Physical Form / Packaging:

PLEXIGLAS® Heatresist FT15 is supplied as pellets of uniform size, packaged in 25kg, two-ply polyethylene bags; other packaging on request.

For more information:

For more information, e.g. Charts or lists of resistance are in the database CAMPUS ® (<http://www.campusplastics.com>) free of charge.

Properties:

	Parameter	Unit	Standard	PLEXIGLAS® Heatresist FT15
Mechanical Properties				
Tensile Modulus	1 mm/min	MPa	ISO 527	3500
Stress @ Break	5 mm/min	MPa	ISO 527	50
Strain @ Break	5 mm/min	%	ISO 527	3.1
Charpy Impact Strength	23°C	kJ/m²	ISO 179/1eU	18
Thermal Properties				
Vicat Softening Temperature	B / 50	°C	ISO 306	115
Glass Transition Temperature		°C	ISO 11357	121
Temp. of Deflection under Load	0.45 MPa	°C	ISO 75	107
Temp. of Deflection under Load	1.8 MPa	°C	ISO 75	105
Classes of construction product			DIN EN 13501-1	E
Flammability UL 94	1.5 mm	Class	IEC 60695-11-10	HB
Glow Wire Ignition Temperature		°C	IEC 60695-2	675
Rheological Properties				
Melt Volume Rate, MVR	230°C / 3.8kg	cm³/10min	ISO 1133	4.5
Optical Properties				
Luminous transmittance	d=3 mm			
Luminous transmittance	D65	%	ISO 13468-2	91
Refractive Index	589nm/23°C		ISO 489	1.502
Other Properties				
Density		g/cm³	ISO 1183	1.19
Recommended Processing Conditions				
Predrying Temperature		°C		100
Predrying Time in Desiccant-Type Drier		h		4 - 6
Melt Temperature		°C		220 - 250
Mold Temperature (Injection Molding)		°C		70 - 95

All listed technical data are typical values intended for your guidance. They are given without obligation and do not constitute a materials specification.

Certified to ISO 9001:2015, ISO 14001:2015 and IATF 16949:2016.

This information and all further technical advice is based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

Röhm is a worldwide manufacturer of PMMA products sold under the PLEXIGLAS® trademark on the European, Asian, African and Australian continents and under the ACRYLITE® trademark in the Americas.

® = registered trademark

PLEXIGLAS and PLEXIMID are registered trademarks of Röhm GmbH.

CAMPUS is a registered trademark of Chemie Wirtschaftsförderungs-GmbH, Frankfurt / M.

Röhm GmbH • Darmstadt • Germany
plexiglas.polymers@roehm.com
www.plexiglas-polymers.com
www.roehm.com

Ref. No.: MC100-E A1142 Date: 2020-02-20